

# HEGSEL® Pox 430

All-Purpose Low Viscosity Epoxy Resin Coating

*You Build, We Protect!*

**Description:**

**HEGSEL Pox 430** is an all-purpose, solvent-free, pigmented, two-component epoxy resin coating for hard-wearing industrial coatings.

**HEGSEL Pox 430** is high-quality adjusted, with very good coverage. Due to the low viscosity the product is suitable for rolled coatings, as well as top sealing coat for scattered, slip resistant coatings.

The material is suitable for smooth coatings for 1 - 4 mm layers. The coating material may be mixed with fire-dried quartz sand (grain size 0.1 / 0.3 mm) up to 0.7 parts by weight. Mixing with quartz sand is useful and economic for layers starting at 2 mm. The coating material has good processing, self-levelling and smoothing properties.

**HEGSEL Pox 430** has well balanced properties and may be used all-purpose. Because the product is multi-purpose and has a wide range of application possibilities the amount of material to be stored may be reduced.

The cured coatings are very resistant to mechanical load and different chemicals. The coating is resistant to water, salt, salt solutions, alkaline and bases, as well as diluted mineral acids, like salt or sulphuric acid. There is also a good resistance to many solvents like benzene, fuel, grease, oil, and so on. Conditional resistance to concentrated mineral acid. Short-term resistance to concentrated and diluted organic acids like formic or acetic acid. Non-durable resistance to chlorinated hydrocarbon, ester, concentrated nitric acid, and others. For special demands to resistance obtain advice.

**HEGSEL Pox 430** is available in different colours. Slight colour alterations may be possible due to technical reasons. Pale colour epoxy resin coatings may show slight colour alterations, which may become visible. For an epoxy resin product **HEGSEL Pox 430** shows only slight colour alterations though.

**Characteristics:**

- Good self-levelling properties
- Suitable even for thin coatings
- All-purpose use
- Coloured glossy surface
- Can be filled with sand
- Water and chemical resistant
- Wear-resistant
- Only slightly yellowing
- Reduced stock
- Solvent-free
- Free of deleterious substances against varnish

**Applications:**

- Thin coatings 0.8 - 1.5 mm for light mechanical load.
- Smooth coatings for commercially used areas with medium mechanical load, e.g. production areas, stacking ground in many economic sectors (2 mm coating).
- Smooth coatings for commercially used areas with high demands on mechanical load, e.g. production areas, stacking ground in many economic sectors (3 - 4 mm coating).
- Plain-coloured top sealer for scattered coatings.
- Pigmented supporting level for decorative, colour-sand scattered coatings and subsequent sealing coats, e.g. with **HEGSEL Pox 476**, **HEGSEL Pox 465**, or even **HEGSEL Pox 430**.
- OS 8 coatings for areas with vehicle traffic and high mechanical load.

**Application Data:**

<b>Mixing Ratio</b>	<b>Parts by Weight</b> <b>Parts by Volume</b>	A : B = 4 : 1 A : B = 100 : 38		
<b>Further Coatings</b>		After curing, but not longer than 48 hours at 20°C		
<b>Consumption</b>	<b>Top Coat</b>	0.550 - 0.900 kg/m <sup>2</sup>		
	<b>Thin Coat</b>	0.8 - 1.5 kg/m <sup>2</sup>		
	<b>Standard Coat</b>	1.3 - 1.5 kg/m <sup>2</sup> for each mm layer		
<b>Colours</b>		Colours available on request!		
<b>@Temperature</b>		<b>10°C</b>	<b>20°C</b>	<b>30°C</b>
<b>Processing Time</b>		70 - 90 min	30 - 35 min	15 - 20 min
<b>Curing Time</b>	<b>Accessibility</b>	24 - 36 hrs	14 - 18 hrs	10 - 14 hrs
	<b>Mechanical Load</b>	-	48 - 72 hrs	-
	<b>Chemical Load</b>	-	7 days	-

**Packaging:**

Hobbock-Combi 30 kg

**Storage:**

12 months in sealed original containers under dry and cool conditions between 10 - 20°C. Bring to a suitable working temperature before application. Tightly re-seal opened containers and use the content as soon as possible.

Protect from heat and freeze!

## 1. Build-up of Coats

### Smooth thin coatings

- Apply base coat with the recommended HEGGEL-Base Coat resin, like **HEGGEL Pox 410**, **HEGGEL Pox 411**, **HEGGEL Pox 412**, **HEGGEL Pox 413**, or **HEGGEL Pox 415**. Consumption approx. 0.3 - 0.4 kg/m<sup>2</sup> depending on the substrate.
- Apply a scratch coat for a planar substrate, e.g. with **HEGGEL Pox 410**, **HEGGEL Pox 411**, **HEGGEL Pox 415**, and **HEGGEL quartz sand-mix 2/1**. Mixing ratio 1 : 0.8 parts by weight, consumption of mixture approx. 0.8 - 1.3 kg/m<sup>2</sup>.
- Apply the coating **HEGGEL Pox 430** with a trowel, consumption 0.8 - 1.5 kg/m<sup>2</sup>.

### Smooth coating medium layer (2 mm)

- Apply a base coat with the recommended HEGGEL-Base Coat resin, like **HEGGEL Pox 410**, **HEGGEL Pox 411**, **HEGGEL Pox 412**, **HEGGEL Pox 413**, or **HEGGEL Pox 415**. Consumption approx. 0.3 - 0.4 kg/m<sup>2</sup> depending on the substrate.
- Apply a scratch coat for a planar substrate, e.g. with **HEGGEL Pox 410**, **HEGGEL Pox 411**, **HEGGEL Pox 415**, and **HEGGEL quartz sand-mix 2/1**. Mixing ratio 1 : 0.8 parts by weight, consumption approx. 0.8 - 1.3 kg/m<sup>2</sup>.
- Apply the coating **HEGGEL Pox 430** with a trowel, consumption 2.6 - 3.0 kg/m<sup>2</sup> for approx. 2 mm coating. Coating can be mixed with quartz sand (0.1/0.3 mm) up to 1 : 0.7.
- Optional: Scatter with silicium carbide, delustering agent or decorative flakes (chips).
- Optional: Seal the surface with a suitable silk gloss or matt-finished sealer like e.g. **HEGGEL Pox 470**, **HEGGEL Flex 530**, **HEGGEL Flex 533** or **HEGGEL Flex 535**.

### Plain coloured scattered coating according to OS 8 with slip resistance grade R11/V4

- If necessary: Apply a base coat with the recommended HEGGEL-Base Coat resin, like **HEGGEL Pox 410**, **HEGGEL Pox 411**, **HEGGEL Pox 412**, **HEGGEL Pox 413**, or **HEGGEL Pox 415**. Consumption approx. 0.350 kg/m<sup>2</sup> depending on the substrate.
- If required: Apply a scratch coat for a planar surface, e.g. with **HEGGEL Pox 410**, **HEGGEL Pox 411**, **HEGGEL Pox 415**, and **HEGGEL quartz sand-mix 2/1**. Mixing ratio 1 : 0.8 parts by weight, consumption approx. 0.8 - 1.3 kg/m<sup>2</sup>.
- Apply **HEGGEL Pox 430** as base coat filler approx. 15 % of quartz sand (0.3/0.8 mm) added, consumption 0.8 kg/m<sup>2</sup>.
- For slip resistance grade R11/V4 scatter completely with quartz sand 0.3/0.8 mm.
- After curing sweep off excess sand, chip off, and vacuum until no more grain of sand is being released.
- Apply **HEGGEL Pox 430** as a top sealer with a rubber squeegee, distribute with a velour roller using criss-cross strokes

and roll off evenly. Consumption approx. 0.6 - 0.7 kg/m<sup>2</sup>.

- Note the recommendations for consumption for the slip resistance grade.

**Note:** The total layer thickness including primer and top-sealer must be of 2.5 mm. For purely protective measures in the sense of DIN EN 13813, it is required only a 1.5 mm layer thickness.

## 2. Surface Preparation

The substrate to be coated has to be levelled, dry, free of dust, has to have adequate tensile and compressive strength, and be free from weakly-bonded components or surfaces. Materials impairing adhesion, such as grease, oil, and paint residues must be removed using suitable methods. Please refer to the product information for the recommended base coats, like **HEGGEL Pox 410**, **HEGGEL Pox 411**, **HEGGEL Pox 412**, **HEGGEL Pox 413**, and **HEGGEL Pox 415**. The surface strength must then be a minimum of 1.5 N/mm<sup>2</sup>.

For concrete, moisture content must not exceed 4.5 CM%, remaining residual humidity. The possibility of moisture ingress from the rear must be permanently excluded. Base coats may not rest for more than 2 days or must be scattered with quartz sand. The surface to be coated should be prepared mechanically, preferably by shot-blasting. The prepared surface has to be primed accurately, saturated, and free of pores. Estimating the substrate according to the necessary sealed state may be difficult, so a scratch coat is recommended for smoothing the surface. If the substrate hasn't been sealed completely, bubbles and pores may appear because of rising air. Conduct a trial if in doubt.

## 3. Mixing

**HEGGEL Pox 430** will be supplied in the correctly measured mixing ratio. Component A has sufficient volume for the entire trading unit. Decant the hardener compound B into the resin completely. Blend with a slow speed mixer (200 - 400 rpm) for 2 - 3 minutes, for a material that is homogeneous and free of streaks. To avoid mixing errors it is recommended to principally empty the mixture into a clean container and mix briefly once again ("to repot").

**Adding quartz sand:** Add after mixing components A and B. Fire dried quartz sand grain size 0.1 / 0.3 mm is suitable. Do not use any quartz flour or sand blend. The amount to be added depends on the thickness of layer, temperature, and type of sand. 1 kg of **HEGGEL Pox 430** may usually be filled with up to 0.7 kg of quartz sand. Adding sand is not recommended for thin coatings because self-levelling properties degrade.

**Adding suspending agent:** For coating concave moldings the material **HEGGEL AD 960** has to be added for a stable adjustment. After mixing components A

and B add 3 - 5 % of the thixotropic agent for a material that is free of streaks and adequately stable. When coating floors with a decline, adding 0.1 - 1.0 % of **HEGGEL AD 960** may be necessary to keep the material in place. Scattering the area with sand is beneficiary.

## 4. Processing / Handling

**Coatings:** Process the material immediately after mixing with a coating knife or trowel by applying an even layer on the prepared surface. The product is adjusted with an optimum of air venting. To upgrade the moistening of the substrate, optimizing the self-levelling properties, and removing any air blows, it is recommended to roll with a spiked roller. Using the spiked roller should be carried out time-delayed – after 10 - 20 minutes. Divide working areas before starting work and always work "fresh-in-fresh" to avoid any shoulders.

Do not scatter too early – optimum point of time is after 10 - 30 minutes at 20°C. Scatter with sand until the area is completely covered. Scattering too late may cause an uneven surface and bald spots may appear later on.

**Top sealer for scattered coatings:** After the base coat has cured, sweep and vacuum off the surface until no more excess quartz sand is released. For a slight slip resistance or reduced depth of roughness subsequently grind the peaks slightly for flattening. Distribute the fresh mixture on the floor. Use a smooth rubber squeegee, trowel, or steel coating knife, depending on the desired amount. Pull off and distribute. Watch for an even application and avoid ponding. Using a coating knife rake results in a smooth surface, soft trowels result in a coarser surface. For an even surface and to avoid bald spots re-roll with a velour roller. Using a roller for application results in a increased coarseness. Always work "fresh-in-fresh".

Floor -and air- temperature must not fall below 10 °C and humidity must not exceed 75 %. The difference in floor -and room-temperature must be less than 3°C so the curing will not be disturbed. If a dew point situation occurs adhesion may malfunction, curing may be disturbed, and spotting may occur. Exposure to water should be avoided within the first 7 days. Curing time applies to 20°C. Lower temperature may increase, higher temperature may decrease the curing and processing time.

If working conditions are not complied with, deviations in the described technical properties may occur in the end product.

## 5. Cleaning

To remove fresh contamination and to clean tools use **Cleaner V20** or **V30** immediately. Hardened material can only be removed mechanically.

## 6. Safety Measure

The product is subject to the hazardous material, operational safety, and transport regulations for hazardous goods.

Refer to the DIN-Safety Data Sheet and the information labelled on the containers!

**GISCODE: RE 1**

## 7. Indication of VOC-Content

(EG-Regulation 2004/42)

Maximum Permissible Value 500 g/L (2010,II,j/lb) Ready-for-use product contains < 500 g/L VOC.

## Technical Data

Title	Standard	Value	Unit
Viscosity (Components A + B)	DIN EN ISO 3219 (23°C)	1800	mPas
Density (Components A + B)	DIN EN ISO 2811-2 (20°C)	1.42	kg/L
Water Absorption	DIN 53495	< 0.2	Weight %
Bending Tensile Strength	DIN EN 196/1	> 45	N/mm <sup>2</sup>
Compressive Strength	DIN EN 196/1	> 55	N/mm <sup>2</sup>
Shore-Hardness D	DIN 53505 (7 days)	80	–
Abrasion (Taber)	ASTM D4060	55	mg

**Note:** Values achieved in sampling are average values. Variation in product specification is possible.

**HEGGEL Pox 430;** Revision No: 1.10 / Last Revision Date: 18.09.2023

All information contained herein is based on the current state of our knowledge and practical experience at the time of release. Therefore, please make sure that this is the latest edition of the Technical Data Sheet. All data are only intended as a guideline for informational purposes and do not constitute a legally-binding warranty of the suitability for a certain purpose of use, due to its dependence on site conditions and possible processing, use and applications. All information contained in this technical datasheet is subject to change without notice.

**HEGGEL GmbH**

Huttropstr. 60  
45138 Essen  
Germany

Tel: +49 201 17003 270

Fax: +49 201 17003 277

E-Mail: [info@heggel.de](mailto:info@heggel.de)

Web: [www.heggel.de](http://www.heggel.de)